

## SPRAY BODY IRIDA COLORED

Technical Data Sheet No 803

**General Technical** Description 2-3 passes

Surface

**Body Primed surfaces** 

VOC compliant with the

Dust free 10min at 23°C(73°F)

Metallic surfaces (Interior Use only)

## Pretreatment / Cleaning of substrate



Clean substrate using a soft cloth and BODY 770 ANTISIL NORMAL / BODY 771 ANTISIL FAST.

Make sure the surface is first wiped dry and then air dried.



Make sure you always use appropriate face protection and good ventilation

**Product Application:** »» Apply two to three medium coats necessary to cover the area waiting 5-10 mins in between each coat. Each coat should appear uniform and air dry before the next one is applied. Clear coat is not needed.

	Shake well before using	Flash Point: -97°C	Remarks: • Always try to use the product in accordance with the specifi-	• Storage shelf life: Store in a cool place and use within 36 months for best
		Specific Gravity:	cations provided.	results.
( <del>AAA</del> )	2-3 coats approximately	0.8 - 1.2 g/cm <sup>3</sup> **	<ul> <li>It can be used by countries that do not adopt the VOC legis-</li> </ul>	+5 to +25 °C (41°F-77°F)
	20-30 microns	<b>Solid Content (No thinner):</b> 11% Weight	lation as well.	
			<ul> <li>Shake thoroughly before use.</li> </ul>	
	Spray at a distance of 25 cm thinly applied coats build up at 5-10 minutes intervals will achieve best results.	VOC (2004/42/EC) This product is an aerosol prod- uct based on its ingredients and its properties. The maximum VOC content in this category is 840 g/L. 2004/42/IIB(e)(840)750	• Shake for 2-3 min after agita- tor ball has started to rattle. After preparing the area to be painted ensure it to be free from dirt, wax, oil etc. Test on a similar surface using a back and forth action.	
	Dust free 10 min at 23°C(73°F) Full hardness within	Theoretical Coverage: - Cleaning of equipment:	• Spray at a distance of 25 cm thinly applied coats build up at 3-5 minutes intervals will achieve best results. Leave for 24 hours to harden.	
	24 hours.		<ul> <li>Optimum operating tempera-</li> </ul>	** Specific Gravity values are

For professional use only. The information displayed on this sheet has been carefully selected through a series of laboratory investigations. It is based on our best knowledge at the time of issue. The data is given for information purposes only. We are not liable for its correctness, accuracy and completeness. It is up to the user to check for newer updates or further information if needed for his intended purpose. The intellectual property of this product, trademarks and copyrights is protected. All rights reserved. The relevant Material Safety Data Sheet and warnings displayed on the label must be read carefully. We may modify and / or discontinue operation of all or portions of this information at any time in our sole discretion, without any notice and assume no responsibility to update the information. All rules set forth in this clause shall apply accordingly for any future changes and amendments.

Issue 2 / 2017, August 2017

dependant on the shade

Easy to use

regulations

Excellent results

Fast drying

Economical to use

Ideal for spot repairs and isolated panel paintings.







ture range 10-25°C (50°F-77°F).