




A brand of BASF –  
We create chemistry

# 568-M 135

568-M 135 68-line variant with 568-17

**Application:**



all applications

**Key Features:**

- good leveling
- fast to assemble
- quick-drying for multicolor painting with 68 Line

**Remarks:**

The substrate should be clean, free of dust, rust, oil and grease.

**Substrates**

- = Very well suited
- = well suited
- = suited in some cases

Steel	Galvanized steel	Stainless steel	Aluminium	Anodized Aluminium	GRP / SMC	PP-EPDM	Glasurit CV - Primer	Glasurit CV - Primer Filler / Filler	Powder coating	Coil-coating	Plywood	Wood	OEM-Paintwork	Old paint work
								●●					○	○

**Safety advice:**

It cannot be ruled out that this product contains particles < 0.1 µm.

The products are suitable for professional use only.

**2004/42/IIIB (d)(420)419:** The EU limit value for this product (product category: IIB.d) in ready to use form is max. 420 g/l. The VOC content of this product is 419 g/l.

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our products, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the products for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein are for general information purpose only; they may change without prior information and do not constitute the agreed contractual quality of the products (product specification). The latest version supersedes all previous versions. You can obtain the latest version from our website at [www.glasurit.com](http://www.glasurit.com) or directly from your sales partner. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.



A brand of BASF –  
We create chemistry

# 568-M 135

568-M 135 68-line variant with 568-17

	<b>Mixing Ratio</b>	4 : 1 : 1 by Volume
	<b>Hardener</b>	922-138, -136
	<b>Reducer</b>	568-17
	<b>Spray viscosity at 20°C</b>	DIN 4: 18-22 s
	<b>Potlife at 20°C</b>	30 min

Application:	Compliant - gravity feed cup	HVLV spray gun	Suction cup	Airless/ Airmix	Pressure pot dbl.-pump
<b>Application pressure</b>	bar	2.2-2.5	2	2.5	2.5
<b>Material pressure</b>	bar				0.8-1.5
<b>Nozzle size</b>		1.3-1.4	1.5	1.7	1-1.1
<b>Voltage</b>	kV				50-80
<b>Number of coats</b>		1.5	1.5	1.5	1.5
<b>Flash off at 20°C</b>	min	without	without	without	without
<b>Film thickness</b>	µm	40-60			

<b>Drying</b>	<b>Overcoatable</b>		<b>Tack-free</b>	<b>Ready for masking</b>	<b>Ready to assemble</b>	<b>Sandable</b>
	Min.	Max.				
<b>Object Temp. 20°C</b>	30 min	8 h	30 min	30 min	30 min	

**Safety advice:**

It cannot be ruled out that this product contains particles < 0.1 µm.

The products are suitable for professional use only.

**2004/42/IIIB (d)(420)419:** The EU limit value for this product (product category: IIB.d) in ready to use form is max. 420 g/l. The VOC content of this product is 419 g/l.

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our products, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the products for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein are for general information purpose only; they may change without prior information and do not constitute the agreed contractual quality of the products (product specification). The latest version supersedes all previous versions. You can obtain the latest version from our website at [www.glasurit.com](http://www.glasurit.com) or directly from your sales partner. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.

# 568-M 135

568-M 135 68-line variant with 568-17



A brand of BASF –  
We create chemistry

## Remark

Pre-spray 1 light coat, then apply 1 wet coat for flow.  
The area to be painted should not exceed 3 m<sup>2</sup>.

## Safety advice:

It cannot be ruled out that this product contains particles < 0.1 µm.

The products are suitable for professional use only.

**2004/42/IIIB (d)(420)419:** The EU limit value for this product (product category: IIB.d) in ready to use form is max. 420 g/l. The VOC content of this product is 419 g/l.

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our products, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the products for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein are for general information purpose only; they may change without prior information and do not constitute the agreed contractual quality of the products (product specification). The latest version supersedes all previous versions. You can obtain the latest version from our website at [www.glasurit.com](http://www.glasurit.com) or directly from your sales partner. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.