

Technical Information

65-10






Blending Reducer


Blend-in reducer for baslac clears 40-

- Blend-in reducer to melt in overspray / overlap areas or to melt in clear coat

Application

	Ready for use
	HVLP spray gun
	Nozzle size 1.3 mm
	Application pressure 2 bar
	Nozzle pressure 0.7 bar
	Number of spraycoats 2 -3 (clear coat fade-out areas)

Drying

	Drying at 20 °C	As recommended for the baslac clear used
---	------------------------	--

Safety advice:

2004/42/IIB(cIII)(780)760: The EU limit value for this product (product category: IIB.cIII) in ready to use form is max 780 g/l of VOC. The VOC content of this product is 760 g/l.

The products are suitable for professional use only.

It cannot be ruled out that this product contains particles < 0.1 µm.

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our products, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the products for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein are for general information purpose only; they may change without prior information and do not constitute the agreed contractual quality of the products (product specification). It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.