

# PerformTOP C 2A54

Clear coat, universal



Improve your productivity with this easy-to-apply clear coat, perfect for a broad range of applications.

- Can be easily and safely processed










Perfection  
made simple



A brand of BASF – We create chemistry

# PerformTOP

## C 2A54 Clear coat, universal

<b>Application:</b>	Advance Series - clear coat especially for ONYX HD basecoat	
<b>Key Features:</b>	<ul style="list-style-type: none"> <li>• Easy to apply clear coat for increased productivity</li> <li>• For a broad range of application</li> </ul>	
<b>Remarks:</b>	Select hardener and reducer according to ambient temperature and size of object to be painted	
<b>Solid Content</b>	59 %	
<b>Density</b>	0.9-1.05 g/cm <sup>3</sup>	
<b>Storage temperatur</b>	5-45 °C	
	<b>2:1+10 %</b>	
 <b>Mixing Ratio</b>	100 % by volume	C 2A54 Clear coat, universal
 <b>Hardener</b>	50 % by volume	H 2A14 Topcoat hardener, fast H 2A24 Topcoat hardener, medium H 2A34 Topcoat hardener, slow
 <b>Reducer</b>	10 % by volume	R 2A14 Thinner, fast R 2A24 Thinner, medium R 2A34 Thinner, slow
 <b>Spray viscosity at 20°C</b>	DIN 4: 19-23 s ISO 4: 45-60 s	<b>Potlife at 20°C</b> 2 h
	 <b>HVL spray gun</b>	 <b>Compliant gravity-feed spray gun</b>
<b>Application pressure</b>	bar	2 2-2.5
<b>Nozzle pressure</b>	bar	0.7
<b>Nozzle size</b>		1.3-1.5 1.3-1.4
<b>Number of spraycoats</b>		1 ½ spray coats (no flash-off between coats required)
<b>Flash-off at 20°C</b>	min	No flash-off before oven drying
<b>Film thickness</b>	µm	40-60
<b>Application Remark</b>		Alternatively: 2 spray coats with app. 3-5 min intermediate flash-off between the spraycoats
<b>Drying</b>		
 <b>Drying at 20 °C</b>		10 h
 <b>Drying at 60 °C</b>		30 min
 <b>Infrared (short wave)</b>		8 min
<b>Drying Remark</b>	<ul style="list-style-type: none"> <li>• Drying times can be influenced by the selection of hardener, thinner and application</li> <li>• Additive A 2A14 SpeedADD can reduce drying times</li> </ul>	
<b>Remark</b>	Polishing after specified drying time and cooling	

**Safety advice:**

2004/42/IIIB(d)(420)419: The EU limit value for this product (product category: IIIB.d) in ready-for-use form is max 420 grams of VOC per liter. The VOC content of this product is 419 g/l.

It cannot be ruled out that this product contains particles < 0.1 µm. The products are suitable for professional use only. For the use of this product please adhere to the actual safety recommendations and the personal protective equipment.

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our products, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the products for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein are for general information purpose only; they may change without prior information and do not constitute the agreed contractual quality of the products (product specification). The latest version supersedes all previous versions. You can obtain the latest version from our website at [www.mmpaint.com](http://www.mmpaint.com) or directly from your sales partner. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.

**R-M Automotive Refinish Paints,  
Z.I. du Merret F-60676 Clermont de l'Oise Cedex,  
Tel. (+33) (0) 3 44 77 77 77**



Perfection  
made simple

A brand of BASF – We create chemistry