
# **Technical** Information

# **FLEXPRO**



Additive to prepare EXTRASEALER WHITE / BLACK for direct application to plastics

Product Category: C 5

## Fields of use

Additive which makes EXTRASEALER suitable for direct application to all paintable plastic substrates normally used in the automotive industry

### **Additional Information**

The addition of FLEXPRO does not produce adhesion to unpaintable pure polypropylene (PP) and polyethylene (PE). The product can also be applied to adjacent e-coated new parts, if necessary.

### **Technical characteristics**

Solids content	Density	
11 % ± 2	0.840– 0.940 g/cm <sup>3</sup>	
Storage temperature min. 5°C to max. 45°C	Shelf life 24 months	

# **Application**

Stir well before use.

# Substrate / Pre-treatment / Cleaning

Clean with PK 700 or PK 1000 using a sanding pad. Clean with PK 1000.


The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our products, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the products for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein are for general information purpose only; they may change without prior information and do not constitute the agreed contractual quality of the products (product specification). The latest version supersedes all previous versions. You can obtain the latest version from our website at www.rmpaint.com or directly from your sales partner. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.

R-M Automotive Refinish Paints, Z.I.du Merret F-60676 Clermont de l'Oise Cedex, Tel. (+33) (0) 3 44 77 77 77, 04/2017



# **Technical** Information

# **FLEXPRO**



	EXTRASEALER WHITE / BLACK D 80 / D 70 FLEXPRO	300% by vol. 100% by vol. 100% by vol.	100 g 23 g 21 g
s	Viscosity at 20°C: ISO 4 cup: DIN 4 cup:	40 to 47 seconds 18 to 20 seconds	
	Potlife: 1 – 2 hours at 20°C		
***	HVLP-gravity-feed spraygun Compliant gravity-feed spraygun	1.3 – 1.5 mm 1.3 – 1.4 mm	0.7 bar at the nozzle 2.5 bar
	Number of spraycoats: Film thickness:	<b>Sealer</b> 1 20 – 35 μm	Sanding filler 2 40 – 60 µm
<u> </u>	Flash-off time 20°C	15 – 20 min. until surface mat	1
	Drying at 60°C	1	25 min.
5		1	P400
e		1	P500 – P800

# **Finishing**

Apply R-M topcoat.

## **Sealer Application**

Plastic parts coated with EXTRASEALER WHITE / BLACK containing FLEXPRO can be over coated without intermediate sanding within 5 days. If necessary, small inclusions can be removed with a fine sanding pad after 20 minutes of drying at 20°C.

# Safety instructions

It cannot be ruled out that this product contains particles < 0.1  $\mu m$ .

The products are suitable for professional use only.

For the use of this product please adhere to the actual safety recommendations and the personal protective equipment.

